



COMPLETE COLOR RANGE SPECIFICATIONS

Color	Opacity	ASTM	BSL	Pigment
Titanium White	●	1	8:8:8	PW.6
Tinting White (Pearl/Titanium)	●	N/T	8:8:8	PW.6, MICACEOUS
Naples Yellow	●	1	7:6-7:6	PW.6, PY.42, PY.74LF
Cadmium Yellow Light	●	1	8:8:8	PY.35
Arylamide Yellow Light	●	1	7:8-7:8:6-7	PW.6, PY.74LF
Cadmium Yellow Medium	●	1	8:8:8	PY.37
Transparent Yellow	○	2	7:8-7:8:6-7	PY.74
India Yellow	○	2	7:8-7:8:6	PY.74, PR.101
Arylamide Yellow Deep	●	1	7:6-7:6	PW.6, PY.65
Cadmium Yellow Deep	●	1	8:8:8	PY.37
Jaune Brillant	●	1	7:6-7:6	PW.6, PY.74LF, PR.9
Naples Yellow Reddish	●	1	7:6-7:6	PW.6, PY.65, PR.9
Orange	●	2	6:5-6:5	PY.65, PO.5, PO.20
Cadmium Orange	●	1	8:8:8	PO.20
Transparent Perinone Orange	○	1	8:8-7:8	PO.73
Red Gold	○	1	7:8-7:8	PY.74, PR.175
Vermilion	●	2	6:5-6:5	PR.188
Transparent Red Oxide	○	1	8:8:8	PR.101
Burnt Sienna	●	1	8:8:8	PBr.7
Light Red Ochre	●	1	8:8:8	PR.101
Cadmium Red Light (Scarlet)	●	1	8:8:8	PR.108
Napthol Red Light	○	1	7:6-7:6	PR.9
Cadmium Red Medium	●	1	8:8:8	PR.108
Pyrrrole Red	●	1	8:8:8	PR.254
Crimson	●	N/T	7:8-6-7:6	PR.170
Napthol Crimson	●	2	6:5-4-5	PR.170

Color	Opacity	ASTM	BSL	Pigment
Permanent Alizarine	○	1	8:8:8	PR.175, PR.122
Permanent Brown Madder	○	1	8:8:7	PR.175
Brilliant Magenta	●	1	8:8:8	PR.122, PW.6
Quinacridone Magenta	○	1	8:8:8	PR.122
Quinacridone Red Violet	○	1	8:8:8	PV.19
Brilliant Violet	●	2	7:8-7:8	PW.6, PV.23RS
Dioxazine Purple	○	2	8:8:8	PV.23RS
Purple	●	N/T	7:6-7:6	PR.9, PB.15.3
Paynes Grey	○	1	8:8:8	PB.29, PBk.7
French Ultramarine Blue	●	1	8:8:8	PB.29
Pacific Blue	●	2	7:8-7	PW.6, PV.23RS, PB.15.3
Cobalt Blue Hue	●	1	8:8:8	PB.29, PW.6, PB.15.3
Cobalt Blue	●	1	8:8:8	PB.28
Pthalo Blue	○	1	8:8:8	PB.15.3
Pthalo Blue (Red Shade)	○	1	8:8:8	PB.15.3
Prussian Blue Hue	○	1	8:8-7:8	PB.15.3, PBk.7
Cerulean Blue	●	1	8:8:8	PB.28, PG.50
Cerulean Blue Hue	●	1	8:8:8	PB.29, PB.15.3, PW.6, PG.7
Pthalo Turquoise	○	1	8:8:8	PB.15.3, PG.7
Cobalt Turquoise Light	●	1	8:8:8	PG.50
Cobalt Turquoise Light Hue	●	1	8:8:8	PW.6, PG.7, PB.15.3
Pthalo Green	○	1	8:8:8	PG.7
Terre Verte	●	1	8:8:8	PBr.7, PB.15.3
Chromium Green Oxide	●	1	8:8:8	PG.17
Forest Green	○	2	7:8-7:8-7:6	PY.74, PB.15.3, PR.101
Cobalt Green Hue	●	2	7:8-7:8-6-7	PW.6, PY.74LF, PG.7

Color	Opacity	ASTM	BSL	Pigment
Silver	○	N/T	8:8:8	MICACEOUS
Copper	●	N/T	8:8:8	MICACEOUS
Pale Gold	○	N/T	7:8-7:8-7:8	MICACEOUS
Rich Gold	●	N/T	8:8:8	MICACEOUS
Permanent Sap Green	○	2	7:8-7:8-6-7	PY.74, PB.15.3
Permanent Green Light	●	1	7:8-7:8-6-7	PY.74LF, PG.7
Olive Green	○	2	7:6-7:6	PY.74, PBk.7
Green Gold	○	2	8:8-7:8	PY.73, PR.176, PB.15.3
Yellow Ochre	●	1	8:8:8	PY.42
Raw Sienna Dark	●	1	8:8:8	PBr.7
India Red Oxide	●	1	8:8:8	PBr.7, P R.9, PR.170
Mars Violet	●	1	8:8:8	PR.101
Burnt Umber	●	1	8:8:8	PBr.7
Raw Umber Yellowish	●	1	8:8:8	PBr.7
Raw Umber	●	1	8:8:8	PBr.7
Brown Black	●	1	8:8:8	PR.101, PBk.7
Red Black	●	2	7:8-6-7:6	PBk.7, PR.9
Mars Black	●	1	8:8:8	PBk.11
Carbon Black	○	1	8:8:8	PBk.7
Green Black	●	1	8:8:8	PG.7, PBk.7
Blue Black (Indigo)	●	1	8:8:8	PBk.7, PB.15.3
Toning Grey Mid	○	1	8:8:8	PW.6, MICACEOUS, PBk.7
Toning Grey Yellowish	●	1	8:8:8	PW.6, MICACEOUS, PBr.7
Toning Grey Pinkish	●	1	8:8:8	PW.6, MICACEOUS, PBr.7